

NASA TECH BRIEF

Marshall Space Flight Center



NASA Tech Briefs announce new technology derived from the U.S. space program. They are issued to encourage commercial application. Tech Briefs are available on a subscription basis from the National Technical Information Service, Springfield, Virginia 22151. Requests for individual copies or questions relating to the Tech Brief program may be directed to the Technology Utilization Office, NASA, Code KT, Washington, D.C. 20546.

Selective Coating for Collecting Solar Energy on Aluminum

The problem:

Coated aluminum substrates used as collectors of solar heat require a high solar radiation absorptance and a very low thermal and infrared emittance. The efficiency of such coatings is determined by the ratio α/ϵ , where α is the absorptance and ϵ is the emittance: the larger this ratio, the higher the collector efficiency. Presently used coatings, which were originally developed for brass, copper, and steel substrates, yield relatively low α/ϵ ratios when applied to aluminum.

The solution:

A new, efficient, black-nickel plating applied to aluminum substrate enhances solar absorptance to 93 percent and reduces the emittance to 6 percent.

How it's done:

Aluminum, unlike other common metals, requires a special treatment to make it receptive to an electroplate. The entire process requires anodizing the substrate in an acid bath to produce a thin porous oxide film, plating the anodized surface with bright nickel, and finally plating the surface with black nickel.

Specifically, an aluminum surface is anodized for 10 minutes in a 350-gram phosphoric acid solution diluted in 1 liter of water. This process is carried out at a current density of 12 A/ft² (130 A/m²) and a bath temperature of 80° F (26° C), using a lead cathode. The anodized substrate then is placed into a nickel bath containing the following:

Nickel sulfate (NiSO ₄ • 6H ₂ O)	10 oz/gal (70 g/l)
Nickel chloride (NiCl ₂ • 6H ₂ O)	8 oz/gal (56 g/l)
Boric acid	5.5 oz/gal (38.5 g/l)

This solution includes special brightener and nonpitting agents constituting 7 percent of the bath volume. The plating process is carried out at a current density of 20 A/ft² (215 A/m²) and a bath temperature of 120° to 140° F (48° to 59° C) for approximately 30 minutes, the time necessary to produce a nickel coating thickness

of approximately 0.5 mil (0.01 mm).

The plated surface then is buffed, cleaned in an alkaline solution, dipped into a 30-percent hydrochloric acid solution, rinsed, and introduced into another nickel bath. The second bath composition contains the following:

Nickel sulfate (NiSO ₄ • 6H ₂ O)	10 oz/gal (70 g/l)
Nickel ammonium sulfate	
[NiSO ₄ (NH ₄) ₂ SO ₄ • 6H ₂ O]	6 oz/gal (42 g/l)
Zinc sulfate (ZnSO ₄ • 7H ₂ O)	5 oz/gal (35 g/l)
Sodium thiocyanate (NaCNS)	2 oz/gal (14 g/l)

Plating is continued for the period of time necessary to produce a surface with a solar absorptance of 0.9 and a thermal or infrared emittance of 0.06. This time is determined empirically. In general, 5 minutes of plating time at a current density of 0.5 A/ft² (5.4 A/m²) are sufficient to produce these optical qualities.

Notes:

1. This process may be of interest to engineers and scientists investigating new sources of energy.
2. Requests for further information may be directed to:
Technology Utilization Officer
Marshall Space Flight Center
Code A&PS-TU
Marshall Space Flight Center, Alabama 35812
Reference: B73-10527

Patent status:

Inquiries concerning rights for the commercial use of this invention should be addressed to:

Patent Counsel
Marshall Space Flight Center
Code A&PS-PAT
Marshall Space Flight Center, Alabama 35812

Source: J. R. Lowery
Marshall Space Flight Center
(MFS-22562)

Category 03, 04, 08